

# BLACK OUT

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	0
% VISIBLE LIGHT REFLECTANCE	5
% SOLAR TRANSMITTANCE	0
% SOLAR REFLECTANCE	34
% SOLAR ABSORBANCE	66
SHADING COEFFICIENT	0.21
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	82
% GLARE REDUCTION	100

*Important: All tested materials were applied on a 3mm clear glass surface in accordance with industry standard tests. The intended purpose of the data provided is for comparison purposes only.*

