

SOLAR BRONZE 20

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	18
% VISIBLE LIGHT REFLECTANCE	46
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	62
% SOLAR ABSORBANCE	27
SHADING COEFFICIENT	0.24
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	79
EMISSIVITY	0.61

Important: All tested materials were applied on a 3mm clear glass surface in accordance with industry standard tests. The intended purpose of the data provided is for comparison purposes only.

