

SILVER/BLUE 15 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	13
% VISIBLE LIGHT REFLECTANCE	31
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	37
% SOLAR ABSORBANCE	52
SHADING COEFFICIENT	0.29
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	75
EMISSIVITY	0.69

Important: All tested materials were applied on a 3mm clear glass surface in accordance with industry standard tests. The intended purpose of the data provided is for comparison purposes only.

