

HP CHARCOAL 05

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	4
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	18
% SOLAR REFLECTANCE	22
% SOLAR ABSORBANCE	60
SHADING COEFFICIENT	0.46
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	61
% GLARE REDUCTION	96

Important: All tested materials were applied on a 3mm clear glass surface in accordance with industry standard tests. The intended purpose of the data provided is for comparison purposes only.

