

QDP CHARCOAL 05

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	6
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	45
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	48
SHADING COEFFICIENT	0.67
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	42
% GLARE REDUCTION	93

Important: All tested materials were applied on a 3mm clear glass surface in accordance with industry standard tests. The intended purpose of the data provided is for comparison purposes only.

