

QDP CHARCOAL 20

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	21
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	48
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	46
SHADING COEFFICIENT	0.71
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	40
% GLARE REDUCTION	77

Important: All tested materials were applied on a 3mm clear glass surface in accordance with industry standard tests. The intended purpose of the data provided is for comparison purposes only.

