

QDP CHARCOAL 35

| | |
|-------------------------------|------|
| THICKNESS OF FILM (MIL) | 1.5 |
| % VISIBLE LIGHT TRANSMITTANCE | 36 |
| % VISIBLE LIGHT REFLECTANCE | 7 |
| % SOLAR TRANSMITTANCE | 52 |
| % SOLAR REFLECTANCE | 7 |
| % SOLAR ABSORBANCE | 41 |
| SHADING COEFFICIENT | 0.73 |
| % ULTRA VIOLET TRANSMITTANCE | <1 |
| % TSER | 27 |
| % GLARE REDUCTION | 60 |

Important: All tested materials were applied on a 3mm clear glass surface in accordance with industry standard tests. The intended purpose of the data provided is for comparison purposes only.

