

SECURITY 12 MIL CLEAR

THICKNESS OF FILM (MIL)	12
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	10
% SOLAR TRANSMITTANCE	78
% SOLAR REFLECTANCE	9
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.95
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	4
% GLARE REDUCTION	0

Important: All tested materials were applied on a 3mm clear glass surface in accordance with industry standard tests. The intended purpose of the data provided is for comparison purposes only.

